



**ATIYEH PAYESH BARAK CHEMICAL COMPANY
(OXsos)**

Marine, Offshore, Industrial & Protective Coatings

Data sheet

OXSOS CLEANSHIP ANTIFOULING 299

Product Description

A tin free polishing antifouling based on specially developed mixture of polymers and pigmented with a combination of biocides. The surface is self-abrasive by a carefully adjusted balance of hydrophobic and hydrophilic binders. This mechanism enables leaching control and allows easy recoating after service life. The product is suitable for vessels trading in coastal and tropical waters.

Physical Properties

<u>Color/Texture</u>	Red Brown (RAL), Pink (RAL) , Dark Brown (RAL) /matt
<u>Volume Solids</u>	54.0 %
<u>Specific gravity</u>	1.70 ± 0.05 gr/ml
<u>Flashpoint</u>	>25°C

	Dry film thickness per coat (μ)	Wet film thickness per coat (μ)	Theoretical spreading rate (m ² /l)
Range	75 – 150	140-280	7.2-3.6
Recommended	100	185	5.4

Note: Specific gravity of paint may vary slightly due to shade difference.

Application Data

<u>Guiding data Airless spray</u>	Pressure at nozzle: 120-180 bar. Nozzle size: 0.41 – 0.60 mm Spray angle: 40 – 80 degrees. Volume of thinner: 0- 3 %.
<u>Brush/Roller</u>	Suitable but airless Spray is preferred. Multicoats may be needed to achieve the Specified dry film thickness. Volume of thinner: 0 – 5 %.
<u>Thinner/ Cleaner</u>	OXSOS Special Thinner T-61. Avoid excessive thinning as it will result in lower Sag resistance and slower cure.

Drying and Recoating Times¹

Substrate temperature	Touch dry	Dry to handle	Hard dry	Dry to recoat	Dry to recoat	Minimum drying time for Undocking ⁽²⁾ -----
				Minimum	Maximum	
10° C	4 hours	8 hours	1 days	10 hours	Indefinite	16 hours
23° C	3 hours	6 hours	1 days	8 hours	Indefinite	12 hours
30° C	2 hours	4 hours	1 days	6 hours	Indefinite	8 hours
40° C	1 hours	3 hours	1 days	4 hours	Indefinite	6 hours

⁽¹⁾: The given data must be considered as guidelines only. The actual drying time/time before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, preceding paint system etc.

⁽²⁾: The surface should be dry and free from fouling and other contaminants prior to over coating. When in doubt, consult your nearest OXSOS office.

Surface Preparation

Coated substrates

The surface must be dry and free from fouling, salts and other contaminants. Remove Salts and dirt by fresh water washing and hard fouling by scraping. Corroded and Damaged areas should be repaired first with an appropriate primer system.

Application Conditions

The temperature of the substrate should be at least 10°C and at least 3°C above the dew point of the air. Temperature and relative humidity should be measured in the vicinity of the substrate. Humidity should be below 80% RH. The maximum recommended surface temperature is approx. 35°C. Higher steel temperature is acceptable provided dry-spray is avoided by proper spray application and extra thinning if required. In extreme cases it may be necessary to reduce film thickness in order to avoid sagging. When applying the paint in confined spaces, provide adequate ventilation during application and drying. The temperature of the mixed paint should be at least 10°C; otherwise extra solvent may be required to obtain a proper application viscosity. The maximum temperature of paint before application should be 40°C.

Storage and Shelf Life

This product has the shelf life of 12 months in storage temperature of 10 -30°C. The cans are to be kept in a dry, cool, well ventilated space and away from source of heat and ignition. Cans must be kept tightly closed.

Worldwide Availability

The product is part of the common OXSOS product range but local availability is subject to confirmation. Although we strive to supply the same product through the world, slight modifications of the product in some cases may be necessary in order to comply with local conditions and national regulations. In such cases an alternative datasheet will issued.

Health and Safety

Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators. As a general rule, avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spraying should be carried out under well-ventilated conditions. This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.

Disclaimer

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product without notice.

Sales & Marketing

[Tel:07791570305](tel:07791570305)

[Fax:07791570605](tel:07791570605)

www.oxsoso.com

Factory:

SECOND ZONE INDUSTRIAL, BUSHEHR, IRAN