



**ATIYEH PAYESH BARAK CHEMICAL COMPANY
(OXsos)**

Marine, Offshore, Industrial & Protective Coatings

Data sheet

OXSOPOXY MARINE SURFACE TOLERANT SEALER 306 HB.

Product Description

A two – pack, modified epoxy designed as a tie coat or sealer on epoxy anticorrosive systems in order to improve the adhesion of subsequent antifouling systems. It can also be recoated with other OXSOS antifouling finishing systems making it therefore a perfect second coat in keel-to-rail anticorrosive system.

Physical Properties

<u>Color/Texture</u>	Gray(RAL)/ Matt
<u>Volume Solids</u>	77%
<u>Specific gravity</u>	1.38 ± 0.05 gr/ml
<u>Flashpoint</u>	>25°C

	Dry film thickness per coat (μ)	Wet film thickness per coat (μ)	Theoretical spreading rate (m ² /l)
Range	75 - 160	100 - 200	10.3-4.8
Recommended	120	155	6.4

Application Data

<u>Mixing ratio</u>	by wt. base to hardener: 88 to 12			
<u>Pot life</u>	10°C: 5 hours	23°C: 3 hours	30°C: 2 hours	40°C: 1 hours
<u>Guiding data Airless spray</u>	Pressure at nozzle: 150 – 250 bar.	Nozzle size: 0.38 – 0.53 mm		
	Spray angle: 40 – 80 degrees.	Volume of thinner: 0 –3%.		
<u>Brush/ Roller</u>	Suitable. Multicoats are required to achieve the specified dry film thickness.			
	Volume of thinner: 1 – 5 %			
<u>Thinner/ Cleaner</u>	OXSO epoxy Thinner T-63. If thinner is necessary, this should be added after mixing of the two Components. Avoid excessive thinning as it will result in lower sag resistance and slower cure.			

Drying and Recoating Times¹

Substrate temperature	Touch dry	Dry to handle	Hard dry	Dry to recoat	Dry to recoat
				Minimum	Maximum with 2-pack finishes
10° C	13 hours	24 hours	10days	32 hours	26 days
23° C	8 hours	18 hours	8 days	20 hours	22 days
30° C	6 hours	14 hours	6 days	15 hours	16 days
40° C	3 hours	10 hours	4 days	13 hours	10 days

(¹): The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, preceding paint system etc.

- The surface should be dry and free from contaminants prior to over coating. If the maximum recoating time is exceeded it may be necessary to roughen the surface to ensure intercoat adhesion. When recoating with single pack products, it is advised to recoat before OxsOVINY is fully cured. When in doubt, consult your nearest OXSOS office.

Surface Preparation

Steel

Oil and grease should be removed by solvent cleaning according to SSPC-SP1. Remove Weld spatter and smooth weld seams and sharp edges as applicable. Abrasive blasting: Min. Sa 2 – ISO 8501:1 Apply **OXSOPOXY MARINE SURFACE TOLERANT SEALER 306** after the steel Has been blasted and the quality of preparation has been approved.

Repair

Existing paint systems should be dry and free from salts and other contaminants. Corroded and /or damaged areas should be blast cleaned to ISO-Sa2 or power tool cleaned to ISO-St3 or Hydro blasted to DW 3 according to STG-2222.

Application Conditions

The temperature of the substrate should be at least 10°C and at least 3°C above the dew point of the air. Temperature and relative humidity should be measured in the vicinity of the substrate. Humidity should be below 80% RH. The maximum recommended surface temperature is approx. 35°C. Higher steel temperature is acceptable provided dry-spray is avoided by proper spray application and extra thinning if required. In extreme cases it may be necessary to reduce film thickness in order to avoid sagging. When applying the paint in confined spaces, provide adequate ventilation during application and drying. The temperature of the mixed paint should be at least 10°C, otherwise extra solvent may be required to obtain a proper application viscosity. The maximum temperature of paint before application should be 40°C.

Storage and Shelf Life

This product has the shelf life of 12 months in storage temperature of 10 -30°C. The cans are to be kept in a dry, cool, well ventilated space and away from source of heat and ignition. Cans must be kept tightly closed.

Worldwide Availability

The product is part of the common OXSOS product range but local availability is subject to confirmation. Although we strive to supply the same product through the world, slight modifications of the product in some cases may be necessary in order to comply with local conditions and national regulations. In such cases an alternative datasheet will issued.

Health and Safety

Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators. As a general rule, avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spraying should be carried out under well-ventilated conditions. THIS product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.

Disclaimer

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product without notice.

Sales & Marketing
[Tel:07791570305](tel:07791570305)
[Fax:07791570605](tel:07791570605)
www.oxsoso.com

Factory:

SECOND ZONE INDUSTRIAL,BUSHEHR,IRAN